

Protectosil® SC CONCENTRATE

Aqueous formulation based on silane chemistry for an easy-to-clean treatment of porous, mineral surfaces.

Registration

Protectosil® SC CONCENTRATE

DSL/NDSL (Canada):	No
PICCS (Philippines):	No
ECL (South Korea):	*
IECSC (P.R. China):	Yes
ENCS (Japan):	*
TSCA/PMN (USA):	Yes, no spray application
AICS (Australia):	*
EINECS/ELINCS (EU):	Yes
* = available on request	

Technical Data

Properties and test methods	Value	Unit	Method
Viscosity (20 °C)	approx. 1.6	mPa.s	DIN 53015
pH (20 °C)	4	-	-
Flash point	> 95	°C	EN 22719
Appearance	Yellowish, slightly cloudy liquid	-	-
Density (20 °C)	approx. 1.06	g/cm ³	DIN 51757

Protectosil® SC CONCENTRATE is suited for an easy-to-clean treatment of many mineral substrates.

Safety and Handling

Before considering the use of **Protectosil®** products please read its Material Safety Data sheet (MSDS) thoroughly for safety and toxicological data as well as for information on proper transportation, storage and use. The Material Safety Data Sheet is available after registration on our website www.dynasylan.com or upon request from your local representative, customer service or from Evonik Industries AG, Product Safety Department, E-MAIL sds-im@evonik.com.

Packaging and Storage

Protectosil® SC CONCENTRATE is supplied in 25 kg PE container, 200 kg plastic lined steel drums, and 1.000 kg bulkcontainer. **Protectosil® SC CONCENTRATE** should only be diluted using demineralized water if needed **Protectosil® SC CONCENTRATE** is not resistant to frost and should be stored at temperatures between 3 °C and 40 °C. **Protectosil® SC CONCENTRATE** has a shelf life of at least 12 months if stored in originally sealed containers.

Properties and Use

- Yellowish to orange, slightly turbid liquid
- Essentially free of volatile organic compounds (VOC)
- Flash point > 95 °C
- pH: 4

Protectosil® SC CONCENTRATE

- treated porous, mineral substrates show very good water and oil repellency
- treated surfaces remain clean for longer times and are more easily cleaned (common liquids like coffee, coke, oils and dark liquids are easily removed)
- weakens the adhesion of chewing gum or posters to e.g. facades
- slows down the growth of microorganisms such as mold and algae
- helps avoid unsightly dark water streaks
- is highly reactive and resistant against alkali
- generates water-vapor-permeable, colorless impregnations
- no formation of sticky silicone films
- can be diluted using demineralized water
- is suited for the treatment of water repellent substrates

Protectosil® SC CONCENTRATE may be used undiluted or may be diluted using demineralized water. The exact amount to be applied, suitable dilution rate and mode of application is highly depending on the porosity of the substrate and should be determined on a small test patch. The long-term efficiency of the described effects can be varied using comparable products such as **Protectosil® SC 30**, **Protectosil® SC 60** or **Protectosil® SC 100**.

It is necessary to do a test patch before each application to determine the exact consumption and to check the compatibility with the substrate.

Application

The facade to be treated must be clean and the surface dry. Dirt, grime, efflorescence, algae and moss must be removed. High pressure or water vapour cleaning is suitable. Water absorbed during cleaning must be allowed to dry so that the surface is dry before application begins. Imperfections such as cracks, cracked joints or defective seams must be repaired using appropriate methods. Mortar used for repairs must be fully cured and surface dry.

The application is recommended if air and substrate temperatures are between 5 °C and 40 °C.

Protectosil® SC CONCENTRATE should not be applied during rain or strong wind.

In the case that a water repellent agent such as **Protectosil® SC CONCENTRATE** or a corrosion inhibitor such as **Protectosil® CIT** have been applied to the substrate, it is recommended to wait at least 5 days before **Protectosil® SC CONCENTRATE** is applied.

If droplets form on the surface they should be evenly distributed using a soft brush. It should be avoided to distribute a dried film with a brush.

In some cases (especially on very coarse and very porous substrates) the easy-to-clean effect of **Protectosil® SC CONCENTRATE** may be enhanced by additional treatments. The amount of product required for the second and all subsequent treatments is considerably less. Several layers should only be applied using HVLP technology and resulting droplets must be rubbed in quickly using a brush or swab to distribute the liquid evenly across the surface.

In the case of polished stone (e. g. marble) simply apply **Protectosil® SC CONCENTRATE** once with a cloth, microfiber glove or other suitable aid by polishing until a liquid film is no longer visible. Significantly less product is required for polished surfaces (about 30 g/m²) compared to rough ones.

Non-absorbent substrates such as, for example, glass, wood, plastic and metal cannot be treated with **Protectosil® SC CONCENTRATE**. Glass, wood and metal are not attacked by **Protectosil® SC CONCENTRATE**. Neither are most plastics used in construction. Therefore covering is normally not necessary. To make sure we recommend to carry out a test. In the worst case, product not absorbed by the substrate may react with atmospheric moisture to form a greasy, glossy silicone resin film, which can easily be removed if cleaned immediately using conventional cleaning agents, or alcohol (check for compatibility of the solvent with the surface).

On horizontal surfaces exposed to traffic (e.g. pavers) the effectiveness of **Protectosil® SC CONCENTRATE** will be reduced over time due to abrasion, requiring reapplication after about 6 months to 2 years.

Plants in the vicinity of the substrate to be treated should be protected against contact with **Protectosil® SC CONCENTRATE**.

Protectosil® SC CONCENTRATE reacts with the interfaces in pores and capillaries of the mineral surface and forms invisible, interfacial compounds. To determine the exact amount to be applied and to check whether previous or following treatments are compatible with the **Protectosil® SC CONCENTRATE** treatment it is recommended to do a small test patch first.

Application Details

Suitable substrates	Approximate consumption
concrete	70 g/m ² (1. coat), 40 g/m ² (2. coat)
sand limestone	80 g/m ² (1. coat), 50 g/m ² (2. coat)
marble and granite (polished)	30 g/m ² (1 coat)
glazed tiles	30 g/m ² (1 coat)
red brick	60 g/m ² (1. coat), 30 g/m ² (2. coat)
mineral plaster	70 g/m ² (1. coat), 70 g/m ² (1. coat),
limestone	80 g/m ² (1. coat), 50 g/m ² (2. coat)

This information and all technical and other advice are based on Evonik's present knowledge and experience. However, Evonik assumes no liability for such information or advice, including the extent to which such information or advice may relate to third party intellectual property rights. Evonik reserves the right to make any changes to information or advice at any time, without prior or subsequent notice. EVONIK DISCLAIMS ALL REPRESENTATIONS AND WARRANTIES, WHETHER EXPRESS OR IMPLIED, AND SHALL HAVE NO LIABILITY FOR, MERCHANTABILITY OF THE PRODUCT OR ITS FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE), OR OTHERWISE. EVONIK SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND. It is the customer's sole responsibility to arrange for inspection and testing of all products by qualified experts. Reference to trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used.

Europe / Middle-East / Africa / Row

Evonik Industries AG

Inorganic Materials
Rodenbacher Chaussee 4
63457 Hanau-Wolfgang
Germany
PHONE +49 6181 59 13636
FAX +49 6181 59 13737
protectosil@evonik.com
www.protectosil.com

Asia / Pacific

Evonik (SEA) Pte. Ltd.

Inorganic Materials
3 Internatioanl Business Park
#07-18, Nordic European Centre
Singapore 609927
PHONE +65 6890 6830
FAX +65 6899 6630
protectosil@evonik.com
www.protectosil.com

Asia / Pacific

Evonik Taiwan Ltd.

Inorganic Materials
Artist Construction Bldg
9F, No. 133
Min Sheng East Road, Sec 3
Taipei, 105 Taiwan, R.O.C.
Taiwan
PHONE +886 227 17 1242
FAX +886 227 17 2106
protectosil@evonik.com
www.protectosil.com

North America

Evonik Corporation

Inorganic Materials
P.O. Box 677
299 Jefferson Road
Parsippany, NJ 07054-0677
USA
PHONE (TOLL FREE) +1 800 828 0919
PHONE +1 973 541 8513
FAX +1 973 541 8503
protectosil@evonik.com
www.protectosil.com

Asia / Pacific

Evonik (Shanghai) Co. Ltd.

Inorganic Materials
55, Chungdong Road
Shanghai 201108
P.R. China
PHONE +86 21 6119 1053
FAX +86 21 6119 1075
protectosil@evonik.com
www.protectosil.com

Asia / Pacific

Evonik Japan Co. Ltd

Inorganic Materials
12th Floor Monolith Building
2-3-1, Nishi-Shinjuku-ku
Tokyo 163-0912
Japan
PHONE +81 353 23 7300
FAX +81 353 23 7399
protectosil@evonik.com
www.protectosil.com

Latin America

Evonik Brasil Ltda.

Inorganic Materials
Alameda Campinas, 579
01404-000 São Paulo-SP
Brazil
PHONE +55 11 3146 4123
FAX +55 11 3146 4148
protectosil@evonik.com
www.protectosil.com

Asia / Pacific

Evonik Korea Ltd.

Inorganic Materials
94, Galsan 1-dong
Bupyeong-gu
Incheon, 403-081, Korea
PHONE +82 32 510 2433
FAX +82 32 505 2510
protectosil@evonik.com
www.protectosil.com

Asia / Pacific

Evonik India Pvt. Ltd.

Inorganic Materials
Krislon House
Saki Vihar Road, Anderi (E)
Mumbai - 400 072
India
PHONE +91 226 7238 800
FAX +91 226 7238 811
protectosil@evonik.com
www.protectosil.com